

SOLITEX FRONTA QUATTRO FB connect

Flame-resistant wall lining membrane for open-jointed cladding, gap width up to 35 mm (1 3/8"), with self-adhesive zones



Technical data

	Substance	
Protective and covering fleece	Polypropylene microfibre	
Membrane	monolithic	
Self-adhesive zones	water-resistant SOLID adhesive	
Property	Regulation	Value
Colour		black
Surface weight	EN 1849-2	145 g/m ² ; 0.48 oz/ft ²
Thickness	EN 1849-2	0.5 mm ; 20 mils
Water vapor resistance factor μ	EN ISO 12572	160
sd value	EN ISO 12572	0,08 m
g value		0.4 MN·s/g
Vapour permeance	ASTM E 96	41 US perms
Fire rating	EN 13501-1	B - s1, d0
Outdoor exposure		4 months
Water column	EN ISO 811	10 000 mm; 32' 10"
Water tightness non-aged/aged*	EN 13859-2	W1 / W1
Watertight joints with 'connect' technology if TESCON VANA is used for sticking	EN 13859-1	W1
Tensile strength MD/CD	EN 13859-2 (A)	260 N/5 cm / 225 N/5 cm ; 30 lb/in / 26 lb/in
Tensile strength MD/CD aged*	EN 13859-2 (A)	260 N/5 cm / 220 N/5 cm ; 30 lb/in / 25 lb/in
Elongation MD/CD	EN 13859-2 (A)	60 % / 80 %
Elongation MD/CD aged*	EN 13859-2 (A)	30 % / 40 %
Nail tear resistance MD/CD	EN 13859-2 (B)	190 N / 220 N ; 43 lbf / 49 lbf
*) Durability after artificial ageing	EN 1297 / EN 1296	passed (for walls with open joints)
Flexibility at low temperature	EN 1109	-40 °C ; -40 °F
Temperature resistance		permanent -40 °C to 80 °C ; -40 °F to 176 °F
Thermal conductivity		0.04 W/(m·K) ; 0.3 BTU-in/(h·ft ² ·F)
CE labelling	EN 13859-2	yes

Application

For use as a wall lining membrane behind closed and open facades (open-jointed cladding up to a gap width of 35 mm (1 3/8")); cladding width = at least 3 x gap width). Installation on boarding, wood-based panels and all mat or panel-shaped thermal insulation materials.

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about the application and construction can be found in the pro clima planning documentation. For queries please call the pro clima technical hotline on +49 (0)6202 278245.

MOLL
bauökologische Produkte GmbH
 Rheinalstraße 35 - 43
 D-68723 Schwetzingen
 Fon: +49 (0) 62 02 - 27 82.0
 eMail: info@proclima.de



Advantages

- ✓ Improved safety: 'not easily flammable', fire classification B-s1, d0 as per EN 13501-1
- ✓ Ensures reliable building components: highly permeable and, at the same time, maximum protection against driving rain
- ✓ Not visible behind open-jointed cladding: black fleece with identification marking in the overlap area
- ✓ Highest possible durability and thermostability thanks to the TEEE membrane
- ✓ 4 months of outdoor exposure
- ✓ Quick and reliable bonding thanks to the integrated 'connect' self-adhesive zones on the long edges of the membrane

General conditions

SOLITEX FRONTA QUATTRO FB membranes should be installed with the black side facing outwards. The membranes are to be installed horizontally in a taut manner with no sagging.

When the product is used behind open-jointed cladding, the gap may be a maximum of 35 mm (1 3/8"). The width of cladding pieces must be at least three times the gap width. The distance between the open-jointed cladding and the membrane must be at least 20 mm (7/8").

Fasteners may not be applied in areas where water run-off is collected.

Additional measures (e.g. covering with tarpaulins) should be taken during the construction phase in the case of buildings that are lived in or buildings that are to be given particular protection. Covering with tarpaulins should also be considered if construction work is to be interrupted for a longer period.

CE
20
EN 13859-2

**UK
CA**

**Made in
Germany** developed and
produced by


The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about the application and construction can be found in the pro clima planning documentation. For queries please call the pro clima technical hotline on +49 (0)6202 278245.

MOLL
bauökologische Produkte GmbH
Rheintalstraße 35 - 43
D-68723 Schwetzingen
Fon: +49 (0) 62 02 - 27 82.0
eMail: info@proclima.de

